

RL6000SA / RL6000SB Stretchtape™ Equivalent
Silicone Rubber Self Fusing Electrical Insulating Tape
500°F / 260°C: Meets MIL-I-22444 & Many OEM Specifications
Self Binding Self-Fusing Tape - High Temperature, Heat & Flame Resistant



- Self-bonds / self fuses / self amalgamating. No sticky residue or adhesive when removed. Starts fusing within minutes, fully bonded within hours. Excellent cold temperature performance. Makes an excellent compression tape.
- Excellent for sealing ends of firesleeve: prevents sleeve from absorbing contamination and wicking liquids. Excellent for wrapping electrical & mechanical connections and splices. Makes clean and neat installations of cables, wires and hoses. Makes an instant separation bumper and provides vibration dampening. Secures insulation to hot air ducting.
- CofC available.
- Rolls are 12 or 20 yards long.
- This tape meets the following specifications:
 DMS 2186, Type 1 / RMS 315, Type 1
 IBM PN 6084744 / MIL – 1-22444
 GE A50493 / AE 26495-001
 GE A50E112 (SB only) / ASNA 5107

RL6000SA / RL6000SB Stretchtape™ Equivalent Silicone Rubber Self Fusing Electrical Insulating Tape			
Part Number	Tape Width Inches / mm	Tape Thickness inches / mm	Price Per Roll
Supported Tape – With Fiberglass Substrate – 15% (SB) or 25% (SA) Maximum Elongation			
T-SR-RL6000SA-12Y-08-XX (12 yard roll)	0.50 / 13	0.020 / 0.51	\$ 56.33
T-SR-RL6000SB-12Y-08-XX (12 yard roll)	0.50 / 13	0.020 / 0.51	\$ 56.33
T-SR-RL6000SA-12Y-12-XX (12 yard roll)	0.75 / 19	0.020 / 0.51	\$ 64.82
T-SR-RL6000SB-12Y-12-XX (12 yard roll)	0.75 / 19	0.020 / 0.51	\$ 64.82
T-SR-RL6000SA-12Y-16-XX (12 yard roll)	1.00 / 25	0.020 / 0.51	\$ 67.29
T-SR-RL6000SB-12Y-16-XX (12 yard roll)	1.00 / 25	0.020 / 0.51	\$ 67.29
T-SR-RL6000SA-20Y-16-XX (20 yard roll)	1.00 / 25	0.020 / 0.51	\$ 112.14
T-SR-RL6000SB-20Y-16-XX (20 yard roll)	1.00 / 25	0.020 / 0.51	\$ 112.14

- For the XX value (color code): OR = Oxide-Red, BK = Black
- 12Y/20Y in part number: 12Y = 12 yard roll length. 20Y = 20 yard roll length

T-SR-RL6000SA-XX equivalent to NSN 5970-01-325-8971. T-SR-RL6000SB-XX equivalent to NSN 5970-00-841-1172

Amalgamating time: At 120°C; 120 minutes / at 150°C; 35 minutes / at 200°C; 20 minutes / at 250°C; 15 minutes

Stretchtape™ is a trademark of Kirkhill-TA / Esterline